

/U1/1

DIALOG(R)File 351:(c) 2004 Thomson Derwent. All rts. reserv.

WPI Acc No: 1983-01758C/

Reduction of exhalation of formaldehyde from chipboards - by spraying hot boards before stacking with ammonia yielding materials

Patent Assignee: FRAUNHOFER-GES FORD ANGE (FRAU); SWEDSPAN AB (SWED-N)

Inventor: MEHLHORN L; ROFFAEL E

Number of Countries: 008 Number of Patents: 004

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
DE 2829021	B	19800103				198002 B
EP 6486	A	19800109				198002
EP 6486	B	19840111				198403
DE 2966525	G	19840216				198408

Priority Applications (No Type Date): DE 2829021 A 19780701

Designated States (Regional): AT; BE; CH; DE; FR; GB; IT; SE

Abstract (Basic): DE 2829021 B

The surface of hot chip or fibre board plates bonded by aminoaldehyde resins, is treated with urea or some other material capable of splitting off ammonia, to reduce the amt. of formaldehyde given off. The materials are applied to the plates immediately or shortly after they are removed from the hot press.

Watery solutions of the urea or other materials are used.

An aq. soln. of 5 to 20% urea may be used and be sprayed on the plates at 10 to 100g solid matter per m2 plate surface, at plate thicknesses from 5 to 50mm. The sprayed plates are stacked whilst hot.

Treatment reduces HCHO evolution without reducing the tensile strength of the boards. At the same time, the surfaces of the boards are left so that they can be coated with pigments or fabrics or laminating papers without difficulty.